

## TECHNICAL DATA SHEET

### Thermobreak<sup>®</sup> Thermaloc

<b>Material:</b>	Crosslinked closed cell polyolefin foam
<b>Nominal Density:</b>	300 kg/m <sup>3</sup>
<b>Thermal Conductivity:</b> (ASTM C518)	0.069 W/m.°K (@ 23°C mean temperature)
<b>Water absorption by volume:</b> (Internal)	<1% w/w
<b>Resistance to fungi:</b> (ASTM G21)	Good
<b>Ozone Resistance:</b>	Excellent
<b>UV Resistance:</b>	Excellent
<b>VOC Emission Rate:</b> (ASTM D5116)	Low VOC emitting ("Green Star")
<b>Compression Strength:</b> (Internal)	850 kPa @ 10% deflection 970 kPa @ 25% deflection 1540 kPa @ 50% deflection
<b>Operating Temperature Range:</b>	-40 °C ~ +105 °C

### ENQUIRIES

If you require any further information, please consult your local distributor or contact us at

#### SEKISUI FOAM AUSTRALIA

1-5 Parraweena Road  
Taren Point  
NSW 2229  
AUSTRALIA

Tel : +61 2 9525 9880  
Fax : +61 2 9525 8004  
Email: [info@sekisuifoam.com.au](mailto:info@sekisuifoam.com.au)  
Web: [www.sekisuifoam.com.au](http://www.sekisuifoam.com.au)

#### THAI SEKISUI FOAM

700/329 Moo 6, Amata Nakorn Industrial Estate  
Tumbol Donhua-loh, Amphur Muang  
Chonburi 20000  
THAILAND

Tel: +66 3821 3219 ~ 26  
Fax: +66 3821 3281  
Email: [info@thaisekisui.co.th](mailto:info@thaisekisui.co.th)  
Web: [www.thaisekisui.co.th](http://www.thaisekisui.co.th)



This information on Sekisui Foam International products is presented to the best of our knowledge. All product data is based on average values and is for guidance only. As these products are subject to constant research and development, we reserve the right to update the contents without notice.

Recommendations as to methods of post fabrication, application and use of Sekisui Foam International products are based on our experience and knowledge of the characteristics of our products and are given in good faith. As producer of the material we have no control over the application of Sekisui Foam International products and no legal responsibility is accepted for such recommendations. In particular, no responsibility is accepted by us for any system in which Sekisui Foam International products are utilised or for any application.

**Sofflon** and **Thermobreak** – Registered trademarks of Sekisui Chemical Co. Ltd or its subsidiaries.

© Sekisui Pilon Pty Ltd. Date of Publication: August 2016.