

TECHNICAL DATA SHEET

Softlon® FR-ND 3000

Description:


Softlon® FR-ND 3000 is a flexible closed cell, electron beam crosslinked, fire retardant polyolefin foam with a smooth outer skin. Due to the unique manufacturing process, Softlon® FR-ND 3000 exhibits consistent thickness and density, and possesses a fine cell structure.

The foam is free of heavy metals, PVC, plasticisers and CFCs. Softlon® FR-ND 3000 is compliant with the requirements of the EU Directive 2011/65/EU, commonly known as the Restriction of Hazardous Substances (RoHS) directive.

| Property | Typical Value | Test Method |
|---------------------------|---|-------------|
| Density | 33 kg/m ³ (nominal) | Internal |
| Tensile Strength | 4.0 kg/cm ² (longitudinal) 2.2 kg/cm ² (crosswise) | JIS K6767 |
| Elongation | 236% (longitudinal) 158% (crosswise) | JIS K6767 |
| Tear Strength | 2.1 kg/cm (longitudinal) 1.2 kg/cm (crosswise) | JIS K6767 |
| Compression Strength | 0.35 kg/cm ² @ 25% 1.00 kg/cm ² @ 50% 3.25 kg/cm ² @ 75% | Internal |
| Compression Set | 7.0% @ 25% deflection | JIS K6767 |
| Dimensional Change Heat | -1.30% (longitudinal) -0.80% (crosswise) | 70°C, 22h |
| Working Temperature Range | -80 / +100 °C | Internal |
| Thermal Conductivity | 0.034 W/m/°K | ASTM C518 |
| Flammability Properties | Pass | UL94 (HF-1) |
| Water Absorption | 0.07 mg/cm ² | JIS K6767 |
| Water Vapour Permeability | 7.3 x 10 ⁻¹⁴ kg/m/s/Pa | JIS Z0208 |

Nomenclature:

The following table explains the nomenclature of Softlon® physically crosslinked polyethylene foams.



Tolerances:

The following tables list tolerances for thickness, density and width of standard Softlon® products:

| Thickness | |
|--------------------------|------------------------------|
| Nominal Thickness | Tolerance¹ |
| 2mm | -0.3mm / +0.3mm |
| 3mm | -0.4mm / +0.4mm |
| 4mm | -0.5mm / +0.5mm |
| 5mm | -0.5mm / +0.6mm |
| 6mm | -0.6mm / +0.8mm |
| 8mm | -0.8mm / +1.0mm |
| 10mm | -1.0mm / +1.5mm |
| 12mm | -1.0mm / +1.5mm |
| 15mm | -1.0mm / +2.0mm |
| 20mm | -1.0mm / +2.0mm |
| 25mm | -1.0mm / +2.5mm |

¹Other thicknesses and/or tolerances subject to confirmation. When unwinding the roll, especially for low density material, the foam near the core may be compressed due to its own weight. After allowing for relaxation, the foam will recover to original thickness.

| Density² (foam only) | |
|--|------------------|
| Nominal Density | Tolerance |
| From 25 – 200 kg/m ³ | ± 10% |

²Applies to the foam core.

| Width³ (Sheet) | |
|----------------------------------|------------------|
| Nominal Width | Tolerance |
| 1000mm | -0 / +20mm |
| 1200mm | |
| 1500mm | |

³Other widths and/or tolerances subject to confirmation.

THAI SEKISUI FOAM

700/329 Moo 6, Amata Nakorn Industrial Estate
Tumbol Donhua-loh, Amphur Muang
Chonburi 20000 THAILAND

Tel: +66 3821 3219 ~ 26, Fax: +66 3821 3281
Email: info@thaisekisui.co.th, Web: www.thaisekisui.co.th



This information on Sekisui Foam International products is presented to the best of our knowledge. All product data is based on average values and is for guidance only. As these products are subject to constant research and development, we reserve the right to update the contents without notice.

Recommendations as to methods of post fabrication, application and use of Sekisui Foam International products are based on our experience and knowledge of the characteristics of our products and are given in good faith. As producer of the material we have no control over the application of Sekisui Foam International products and no legal responsibility is accepted for such recommendations. In particular, no responsibility is accepted by us for any system in which Sekisui Foam International products are utilised or for any application.

Softlon and **Thermobreak** – Registered trademarks of Sekisui Chemical Co. Ltd or its subsidiaries.

© Sekisui Pilon Pty Ltd. Date of Publication: August 2016.