

TECHNICAL DATA SHEET

G60 Pressure Sensitive Adhesive

Description:

G60 is a general purpose solvent based acrylic emulsion tissue tape. It provides excellent permanent adhesion and very strong initial tack at room and elevated temperatures.

Adhesive System:	Solvent based acrylic
Thickness:	0.09 mm
Carrier:	Tissue paper 14 g/m ²
Release Liner:	95 g/m ² Kraft paper PE and silicone coated both sides

Product Features:

- Excellent bonding to low surface energy substrates.
- It offers excellent water and solvent resistance.
- It can be re-positioned thus allowing alignment with substrate.
- It features a moderate weight release liner with easy-peel properties for ease of application.

Property	Typical Value	Test Method
Initial Tack, 14mm steel ball	< 100 mm	GB/T 4852
Adhesion to Steel	1.6 kg / 25 mm	GB/T 2792
Holding Power 1kg load on 25mm x 25mm	> 800 minutes	GB/T 4851
Service Temperature	-5 / +80 °C	Internal
Intermittent Temperature	+ 120 °C	Internal

Surface Preparation:

It is essential for pressure sensitive tapes that the surface to which the tape is applied is clean and free of grease and oil. Suitable cleaning solvents are acetone and methylated spirits.

THAI SEKISUI FOAM

700/379 Moo 6, Amata Nakorn Industrial Estate
Tumbol Donhua-loh, Amphur Muang
Chonburi 20000 THAILAND

Tel: +66 3821 3219 ~ 26, Fax: +66 3821 3281

Email: info@thaisekisui.co.th, Web: www.thaisekisui.co.th



This information on Sekisui Foam International products is presented to the best of our knowledge. All product data is based on average values and is for guidance only. As these products are subject to constant research and development, we reserve the right to update the contents without notice.



Recommendations as to methods of post fabrication, application and use of Sekisui Foam International products are based on our experience and knowledge of the characteristics of our products and are given in good faith. As producer of the material we have no control over the application of Sekisui Foam International products and no legal responsibility is accepted for such recommendations. In particular, no responsibility is accepted by us for any system in which Sekisui Foam International products are utilised or for any application.



Softlon and **Thermobreak** – Registered trademarks of Sekisui Chemical Co. Ltd or its subsidiaries.

© Sekisui Pilon Pty Ltd. Date of Publication: October 2019.