

TECHNICAL DATA SHEET

Thermobreak[®] RT-N

Material:	Physically (irradiation) crosslinked closed cell polyolefin foam with factory applied reinforced facing (electrically non-conductive) and pressure sensitive adhesive backing
Density:	25 kg/m ³ (foam core only)
Thermal Conductivity: (ASTM C518)	0.032 W/m.°K (@ 23°C mean temperature)
Water Vapour Permeability: (ASTM E96)	5.7 x 10 ⁻¹⁴ kg/Pa.s.m (0.21 mg.m/N.h)
Water Vapour Permeance:	4.77 x 10 ⁻³ g/MN.s
Permeability Resistance Factor:	μ > 3,000
Water Absorption by Volume: (ASTM C1763, Procedure B, 24h)	< 0.2% v/v
Resistance to Fungi: (ASTM G21)	Zero Growth
Ozone Resistance:	Excellent
UV Resistance:	Excellent
VOC Emission Rate: (ASTM D5116)	Low VOC emitting ("Green Star")
Operating Temperature Range:	-80 °C ~ +100 °C

FIRE AND SMOKE PERFORMANCE

ISO 5658 Part 2	Flame Spread	COMPLIES (UN ECE R118) COMPLIES (EN 45545-2 R1, HL1 RATING)
ISO 5659 Part 2	Smoke Toxicity Smoke Density	COMPLIES (EN 45545-2 R1, HL1 RATING) COMPLIES (EN 45545-2 R1, HL1 RATING)
ISO 5660 Part 1	Heat Release Rate	COMPLIES (EN 45545-2 R1, HL1 RATING)

TOLERANCES

The following tables list tolerances for thickness, density and width of standard Thermobreak[®] RT products:

Thickness	
Nominal Thickness	Tolerance
5mm	-0.5mm / +1.0mm
6mm	-0.5mm / +1.5mm
8mm	-1.0mm / +1.5mm
10mm	-1.0mm / +1.5mm
12mm	-1.0mm / +1.5mm
Other thicknesses and/or tolerances subject to confirmation.	

Density* (foam only)	
Nominal Density	Tolerance
25 kg/m ³	± 10%
*Applies to the foam core. The density of Thermobreak with reinforced aluminium foil will be higher.	

Width (Sheet)	
Nominal Width	Tolerance
1200mm	-0 / +20mm
Other widths and/or tolerances subject to confirmation.	

COUNTRY OF MANUFACTURE

Thermobreak[®] RT-N insulation is manufactured in Thailand.

ENQUIRIES

If you require any further information, please consult your local distributor or contact us at

SEKISUI FOAM AUSTRALIA

1-5 Parraweena Road
Taren Point
NSW 2229
AUSTRALIA

Tel : +61 2 9525 9880

Fax : +61 2 9525 8004

Email: info@sekisuifoam.com.au

Web: www.sekisuifoam.com.au

THAI SEKISUI FOAM

700/379 Moo 6, Amata Nakorn Industrial Estate
Tumbol Donhua-loh, Amphur Muang
Chonburi 20000
THAILAND

Tel: +66 3821 3219 ~ 26

Fax: +66 3821 3281

Email: info@thaisekisui.co.th

Web: www.thaisekisui.co.th



This information on Sekisui Foam International products is presented to the best of our knowledge. All product data is based on average values and is for guidance only. As these products are subject to constant research and development, we reserve the right to update the contents without notice.

Recommendations as to methods of post fabrication, application and use of Sekisui Foam International products are based on our experience and knowledge of the characteristics of our products and are given in good faith. As producer of the material we have no control over the application of Sekisui Foam International products and no legal responsibility is accepted for such recommendations. In particular, no responsibility is accepted by us for any system in which Sekisui Foam International products are utilised or for any application.

Softlon and **Thermobreak** – Registered trademarks of Sekisui Chemical Co. Ltd or its subsidiaries.

© Sekisui Pilon Pty Ltd. Date of Publication: March 2019.